1,932 7,3856

PHYSICAL AND CHIMICAL PROPERTIES OF ROSIN

Builder of agricultural chemistry

and enothseting. Naval stores responsiful from the publicat

The available data on the physical and chemical properties of rosin is rather limited in scope, and a number of discremancies have been found indicating that some of the data may have been obtained on too few or on unusual samples. The following deta have been assembled from sources considered reliable.

Gum Rosin

Gum rosin is composed largely of varying proportions of resin acids and their esters (usually 90-95 per cent) together with unsaponifiable nonacid bodies, which are usually referred to as resenes. Therefore it is to be expected that there will be appreciable variations in the so-called constants and the physical and chemical properties. It is believed that the ranges given for the various properties will include all authentic samples, and permit all properly determined results on normal rosin to fell within the limits. For most rosins, however, the constants fell within ranges which are relatively narrower. With the exception of color, there is not a great difference in the constants for high and low grade rosin, which so frequently overlap that variations in the ranges can be given only for the everages. For gum rosin the properties end constants should fell within the following limits.

Melting Point (so-celled): Capillary tube method: 60-76°C. (140-168°F.) Thermometer bulb drop method: About 10° C. higher than by capillary tube method.

Acid Value: 158-172 (the lighter grades usually have slightly higher acid values).

Seponification Value: 167-184 (see note for acid value)

Unsaponifiable matter: 5.6 - 10.7% (There is no apparent relation between grade and per cent of unsaponifiable).

Ash: 0.015-0.10% (For samples free from excessive dirt. Commorcially clean rosin has an everage ash of 0.020%. The ash consists chiefly of silica and iron oxide).

Iodine Number (Wijs method): 205-230. B and D Rosin usually have low iodine numbers. Other grades everage about 222. The pale grades tend to have higher idding numbers PY than the lower grades. RECEIVED

Specific Gravity: 1.05-1.09.

APR 3 1941 A U.S. Dewartment of Agriculture Refractive Index: 1.546 - 1.548 at 20° C. (68°F.) The higher grades usually have the lower refractive index.

Specific Heat: 0.48 (average for temperature 86° -266°C.)

Ignition Temperature or Fire Point: Around 465°F.

The contract of the contract o

Toluol Insoluble: Although this is not a constant or property, it is often determined as a measure of the foreign matter (sands, bark, dirt, etc.), and varies considerably. Well strained rosin usually does not exceed 0.05% toluol insoluble.

A CONTRACT OF A COMPANY OF THE PARK OF THE

WOOD ROSIN

The following data are for normal untreated wood rosin of FF grade:

Melting Point:

Capillary tube method -- 55-62°C. Thermometer bulb drop method.

Acid value: 150-158

Seponification Value: 162-168

Unsaponifiable: 8.5-14.0%

Iodine Number (Wijs method): 214-218.

Refractive Index: 0.547 at 20° C. (68°F.)

Ash: Less then 0.05%

Density (specific gravity): 1.089 at 20° C.; 0.93 at 238° C.

Mean Specific Heat: 0.477 (20-135°C.)

Coef. of Cub. Expension: $6.37 \times 10^{-4} (0^{\circ} - 100^{\circ} \text{C.})$ 6.80 x 10 (0° - 200° C.)

Latent Hest Vaporization: 1014 btu. per pound at 253°C.

Viscosity: The viscosity of rosin is dependent on its temperature. The following formula has been proposed for calculating the viscosity of American gum and wood rosin, which has not had special treatment.

$$log V = \frac{6.05 t_m - 54}{t - 20} - 3.50*$$

in which log V = common logarithm of the viscosity in poise $t_m \,=\, \text{melting point in °C. as determined by the drop method.}$

T = temperature in °C. at which viscosity is desired.

The higher grades of wood rosin (WWWK) have acid and saponification numbers and unsaponifiable nearer the range of gum rosin than the FF wood rosin. The following data are reported by the manufacturers of wood rosin for the higher grades:

Acid value: 161-170.

Saponification value: 167-174.

Unsaponifiable: 6.0 - 10.0%

*(H. E. Nash, Jour. Ind. Eng. Chem., 24, 2 (1932), p. 177).

at the second second of the second of the